

ACRYLIC PRIMER



Acrylic Primer is a ready to use primer for use on porous and difficult substrates prior to tiling or screeding, or to seal gypsum plasters or screeds prior to the addition of cement based adhesives. It can be used neat when sealing substrates or diluted with an equal quantity of water for general priming.



WATER-BASED POLYMER EMULSION
READY TO USE PRIMER
IMPROVED ADHESION
COLOURED TO INDICATE APPLICATION

TECHNICAL INFORMATION:

PRODUCT INFORMATION	
FORM:	Liquid
COLOUR:	Pink
SPECIFIC GRAVITY:	1 – 1.1 g/ml
pH:	7 – 8
SOLUBILITY:	Miscible with water
BOILING POINT:	100°C (Water based)
FLASH POINT:	No Risk
COVERAGE:	When used neat: 1 Litre will cover approx. 7 - 10 m ² . When diluted 1:1 with clean water: 1 Litre will cover approx. 14 - 20 m ² .

DIRECTIONS FOR USE:

AS A PRIMER

Acrylic Primer should be used to prime all dense and porous surfaces prior to application of any of the range of Larsen Tile Adhesives or the range of Larsen Flooring products. On porous surfaces where the requirement is not to seal the surface, dilute Acrylic Primer 1:1 with clean water and apply adhesive/screed, etc. while primer is still tacky. (Do not allow to dry.) Particularly porous substrates may require a second coat applied after the first has been allowed to dry.

When using Acrylic Primer to seal surfaces, e.g. Gypsum plaster, apply the first coat diluted 1:1 with water and allow to dry, before applying a second coat neat to the surface (do not allow neat primer to pond). 2 or more coats of neat primer may be required. Subsequent products should be applied when the Acrylic primer has dried clear but remains tacky, this is typically within 1 – 2 hours after. Normal practice when applying 2 coats would be to apply the first coat in the evening and the second coat on the following morning prior to tiling or screeding.

RESTRICTIONS

When Acrylic Primer is applied neat, care must be taken to ensure skinning of the product and eventual delamination does not occur. All work should be carried out to current best practice. Priming should never be used in an attempt to improve a poor or failing substrate. If applied acrylic primer is allowed to fully dry out/cure for several days, subsequent adhesion may be impaired.

CLEANING

Clean tools, equipment, etc. using cold water.

STORAGE

Acrylic Primer should be stored in closed containers protected from extremes of temperature.

SHELF LIFE

12 months in unopened manufacturer's containers.

PACKAGING

1L and 5L packs.